

Cox Sales Company
2035 Cook Drive
Salem, Virginia 24153 USA
Phone: (540) 345-2636 FAX: (540) 342-8684

CoxTack 258-5 Re-pulpable Adhesive

Typical Physical Properties:

Percent Solids:	37 TO 40%
Polymer Type:	Acrylic
Brookfield Viscosity: RVT #3 @ 20rpm	500 TO 1,500 cps
pH Value:	6.5 to 8.5
Stabilization System:	Anionic
Appearance (wet):	Milky White
Density, lbs/gallon:	8.6
Odor:	Slight Acrylic
Film Appearance (dry):	Clear

Typical Performance Properties:

Peel Adhesion 180° /SS (stainless steel/wood free paper)	>2.64 lbs/in
Static Shear: (1" x 1" x 1kg @ 40°C)	>20 minutes
FDA Regulations Title 21 CFR Status:	175.105

Description:

Coater-ready pressure sensitive acrylic adhesives.

Suggested Uses:

Water soluble paper labels.

Characteristics:

High peel and moderate shear performance. Protect coated substrates from exposure to moisture and humidity. Adhesion properties will change over time. Product not suitable for acid-free paper stock.

Recommended Storage:

Protect from freezing. Recommended storage temperature is 60°F to 80°F (15°C to -25°C). Keep in tightly covered container.

Shelf Life:

Six months from date of manufacture.

Packaging:

One-way drums, totes or bulk shipments are available.

DOT Label Required:

This product is not classified as a hazardous product under DOT or OSHA regulations. It does not contain any hazardous components at levels which have implications for labeling under these regulations.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.