

Cox Sales Company
2035 Cook Drive
Salem, VA 24153 USA
Phone: (540) 345-2636 FAX: (540) 342-8684

U-120-2
Two Part Urethane
Adhesive / Encapsulant

Typical Technical Data:

Part A: Color:	Amber Liquid
Specific Gravity:	1.08
Viscosity:	4000 cps
Part B: Color:	Amber Liquid
Specific Gravity:	1.02
Viscosity:	200 cps
Mixed: Color:	Amber Liquid
Specific Gravity:	1.03
Viscosity:	<10,000 cps
Mix Ratio: By Weight:	100.0 : 100 B
Gel time, 20g @ 100°C:	20 minutes
Cure Time @ 23C	7 days
Cure Time @ 80C	4 hours
Shore Hardness @23C:	30-40 A
Shore Hardness @ 100C	25-35 A
Shelf Life:	1 year